

## Technical Data Sheet

### SIPOLPRENE® 35150

#### DESCRIPTION

SIPOLPRENE® 35150 is a block ether ester thermoplastic elastomer (TPC-ET), developed and manufactured by Sipol, with a nominal hardness of Shore D 37, a low modulus, and a rheological behaviour that makes it suitable for injection moulding and extrusion processing.

SIPOLPRENE® 35150 has been specifically developed with a low melting point which makes it suitable for blending with PVC to make soft compounds plasticizer free.

SIPOLPRENE® 35150 comes in a natural colour with a standard stabilisation package fully in compliance with European EU 10/2011 Food Contact Regulations. Black colour and/or UV stabilised and/or heat stabilised are all available in dry blend versions upon request.

#### THERMAL PROPERTIES

PROPERTY	TEST METHOD	M.U.	TYPICAL VALUE
Melting temperature	ISO 11357-3	°C	150
Crystallization temperature	ISO 11357-3	°C	74
Glass transition temperature	ISO 11357-2	°C	-55
Vicat A /50	ISO 306	°C	105

#### RHEOLOGICAL PROPERTIES

PROPERTY	TEST METHOD	M.U.	VALUE
MFI 190°C, 2.16kg	ISO 1133	g/10 min	9
MVR 190°C, 2.16	ISO 1133	cm <sup>3</sup> /10min	8

#### MECHANICAL PROPERTIES

PROPERTY	TEST METHOD	M.U.	TYPICAL VALUE
Shore D hardness, instantaneous / 15 s	ISO 868	Shore D	37/33
Stress at break	ISO 527	MPa	28
Elongation at break	ISO 527	%	570
Flexural modulus	ISO 178	MPa	50
Izod impact resistance/notched (23°C)	ISO 180	J/m	No break
Izod impact resistance/notched (-40°C)	ISO 180	J/m	No break
Abrasion resistance (Vertical load 5N)	ISO 4649	mm <sup>3</sup>	33
Compression set (23°C)	ISO 815:1991	%	24
Compression set (70°C)	ISO 815:1991	%	76

#### OTHER PROPERTIES

PROPERTY	TEST METHOD	M.U.	TYPICAL VALUE
Density	ISO 1183	g/cm <sup>3</sup>	1,15
Water absorption (23°C x 24 h immersion)	MI 08	%	0.7

## Technical Data Sheet

### SIPOLPRENE® 35150

#### PROCESSING CONDITIONS

Suggested temperature profile for injection molding

MELTING TEMPERATURE	MOLD TEMPERATURE	NOZZLE	FRONT ZONE 3	CENTER ZONE 2	REAR ZONE 1
°C	°C	°C	°C	°C	°C
150	20 - 30	175	165	155	130-145

Suggested temperature profile for extrusion

MELTING TEMPERATURE	MFI	FEEDING ZONE	COMPRESSION ZONE	METERING ZONE	HEAD/DIE
°C	g/10 min.	°C	°C	°C	°C
150	9 (190 °C, 2.16 Kg)	140 - 150	150 - 160	155 - 170	155 - 170

#### DRYING CONDITIONS

Drying recommended = Yes  
Drying temperature = 90 °C  
Drying time, dehumidifier dryer = 2-3 h  
Processing moisture content = 0,15%

#### PACKAGING

25 kg bags equipped with an aluminum film barrier against moisture action.  
500 kg cardboard octabins equipped with an inner PE liner.  
500 Kg and 1000 Kg big bags.

#### STORAGE

Product is stable for 12 months when stored unopened in its original packaging, kept in a cool and dry place and protected from light. When stocked around 5 – 10°C or below, it is recommended to keep it at 15 – 20°C for at least for 24 hours before using it.