

Technical Data Sheet

Provisional

SIPOLPRENE® S 4682

DESCRIPTION

SIPOLPRENE® S 4682 is an experimental thermoplastic copolyester (TPC) with a content of renewable resources of 51% calculated according to ASTM D6866. It is developed and manufactured by Sipol, with a nominal hardness of Shore D 46, a very low modulus and a rheological behaviour, which makes it suitable for injection molding.

SIPOLPRENE® S 4682 comes in a natural colour with a standard stabilisation package, fully in compliance with American FDA and European EU 10/2011 Food Contact Regulations.

THERMAL PROPERTIES

PROPERTY	TEST METHOD	M.U.	TYPICAL VALUE
Melting temperature	ISO 11357-3	°C	183
Crystallization temperature	ISO 11357-3	°C	146
Glass transition temperature	ISO 11357-2	°C	-37
Vicat A /50	ISO 306	°C	137

RHEOLOGICAL PROPERTIES

PROPERTY	TEST METHOD	M.U.	VALUE
MFI 230 °C, 2.16 Kg	ISO 1133	g/10 min	12
MVR 230 °C, 2.16 Kg	ISO 1133	cm ³ /10min	10

MECHANICAL PROPERTIES

PROPERTY	TEST METHOD	M.U.	TYPICAL VALUE
Shore D hardness, instantaneous / 15 s	ISO 868	Shore D	46/43
Stress at break	ISO 527	MPa	29
Elongation at break	ISO 527	%	420
Flexural modulus	ISO 178	MPa	98
Abrasion resistance (Vertical load 5N)	ISO 4649	mm ³	32
Izod impact resistance/notched (23°C)	ISO 180	J/m	No break
Izod impact resistance/notched (-40°C)	ISO 180	J/m	No break
Compression set (23°C)	ISO 815:1991	%	34
Compression set (70°C)	ISO 815:1991	%	73
Molding shrinkage (perpendicular to flow)	ISO 294-4	%	1.6

Technical Data Sheet

Provisional

SIPOLPRENE® S 4682

CHEMICAL RESISTANCE

CHEMICAL AGENTS	EXPOSURE (Days, RT)	TEST METHODS	U.M.	VALUE
Antifreeze	14	ASTM D 543	A_B_C_NR	B
Ethanol	14	ASTM D 543	A_B_C_NR	B
Hydraulic oil	14	ASTM D 543	A_B_C_NR	B
Mineral oil	14	ASTM D 543	A_B_C_NR	B
Soap solution	14	ASTM D 543	A_B_C_NR	B
Isododecane	14	ASTM D 543	A_B_C_NR	B

A: excellent resistance; B: good resistance; C: Poor resistance; NR: not resistance

OTHER PROPERTIES

PROPERTY	TEST METHOD	M.U.	TYPICAL VALUE
Density	ISO 1183	g/cm ³	1,14
Water absorption (23°C x 24 h immersion)	MI 08	%	0.20
Breathability	MI 18	g/(m ² x24h)	1.8
Hydrolysis resistance (Fluidity increase after 7 days immersion at 80 °C)	MI 20	%	69
Renewable source content (calculated according to ASTM D6866)	ASTM D6866	% (Bio C/Total C)	51

PROCESSING CONDITIONS

Suggested temperature profile for injection molding

MELTING TEMPERATURE	MOLD TEMPERATURE	NOZZLE	FRONT ZONE 3	CENTER ZONE 2	REAR ZONE 1
°C	°C	°C	°C	°C	°C
183	25 - 35	195	190	185	175

Suggested temperature profile for extrusion

MELTING TEMPERATURE	MFI	FEEDING ZONE	COMPRESSION ZONE	METERING ZONE	HEAD/DIE
°C	g/10 min.	°C	°C	°C	°C
183	23 (230°C, 2.16 Kg)	175 - 190	185 - 195	190 - 205	190 - 205

Technical Data Sheet

Provisional

SIPOLPRENE® S 4682

DRYING CONDITIONS

Drying recommended = Yes
Drying temperature = 90 °C
Drying time, dehumidifier dryer = 2-3 h
Processing moisture content = 0,15%

PACKAGING

25 kg bags equipped with an aluminum film barrier against moisture action.
500 kg cardboard octabins equipped with an inner PE liner.
500 Kg and 1000 Kg big bags.

STORAGE

Product is stable for 12 months when stored unopened in its original packaging, kept in a cool and dry place and protected from light. When stocked around 5 – 10°C or below, it is recommended to keep it at 15 – 20°C for at least for 24 hours before using it.