

Via L. Da Vinci, 5 – 27036 MORTARA (PV) - ITALY
Tel. +39 0384 295237 – Fax +39 0384 295084
E-mail: sipol@sipol.com – www.sipol.com
Cap. Soc. € 600.000 i.v. – R.E.A. PV n. 225329
Reg. Imprese di Pavia PV/C.F. 01669490037

P.I. 01842120188

## **Technical Data Sheet**

# TECHNIPOL® 200 P

#### **DESCRIPTION**

TECHNIPOL® 200 P is a copolyester based polymer of white colour in powder form. It has been developed for use as a support polymer in the preparation of master batches for the coloration of resins used in the food packaging sector. It facilitates dispersion; it is non-toxic and does not contain harmful volatiles.

#### **TECHNICAL CHARACTERISTICS**

PROPERTY		TEST METHOD	M.U.	VALUE
Density		ISO 1183	g/cm³	1,28
Medium granulometry		ISO 565 1990	μm	650
Melting temperature		ISO 11357-3	°C	200
MFI	240°C, 0.325kg	ISO 1133	g/10 min	35

### **PACKAGING**

20 kg LDPE bags

#### **STORAGE**

Product is stable for 12 months when stored unopened in its original packaging, kept in a cool and dry place and protected from light. When stocked around 5 – 10°C or below, it is recommended to keep it at 15 – 20°C for at least for 24 hours before using it.