

Via L. Da Vinci, 5 – 27036 MORTARA (PV) - ITALY
Tel. +39 0384 295237 – Fax +39 0384 295084
E-mail: sipol@sipol.com – www.sipol.com
Cap. Soc. € 600.000 i.v. – R.E.A. PV n. 225329
Reg. Imprese di Pavia PV/C.F. 01669490037

P.I. 01842120188

## **Technical Data Sheet**

## **TECHNIPOL® PA 167**

#### DESCRIPTION

TECHNIPOL® PA 167 is a thermoplastic adhesive co-polyamide based of amber colour, extruded into rod shape and used by the automatic lasting machines in the footwear industry. Thanks to its quick setting time, its good flexibility, its excellent wettability and its high adhesion to leather and to both synthetic and regenerated materials, TECHNIPOL® PA 167 is the ideal adhesive for the shoe manufacturing.

Due to the wide variety of materials used in the today's footwear construction, it is recommended to run some preliminary trials in order to homologate the TECHNIPOL® PA 167.


Finally, TECHNIPOL® PA 167 contains more than 80% of raw materials coming from renewable resources (non-edible).

#### **TECHNICAL CHARACTERISTICS**

PRC	PERTY	TEST METHOD	M.U.	VALUE
Diameter		-	mm	3,9 ± 0,1
Density		ISO 1183	g/cm³	0,98
Softening point		MI 13	°C	172
Indicative application temperature		-	°C	220-240
Viscosity Brookfield	232°C	MI 12	Pa*s	3.5

Cone/ plate Viscometer, Model Brookfield CAP 2000+.

### **VISCOSITY vs TEMPERATURE CURVE**



Version N°: 3.EN Revision n° 0 Revision date: 03/08/2022

The information provided herein corresponds to our current knowledge on date of publication. This information may be subject to review, if further experience and knowledge become available. The data reported corresponds to typical values and should not be considered as specification limits, or as a basis for design calculations. This data sheet must not in any way be construed as a license or as an invitation or permission to violate any existing patents, the existence of which must be verified by the Customer. The application, use and processing of Sipol products and the quality of the final products obtained by the customer are completely out of our control. The Customer is responsible for verifying that the material is suitable for the specific application; any data given here does not relieve the Customer from conducting appropriate checks and testing. Sipol cannot foresee all possible variations in actual end-use conditions, and therefore offers no warranty and assumes no liability in connection with any use of this information.





Via L. Da Vinci, 5 – 27036 MORTARA (PV) - ITALY
Tel. +39 0384 295237 – Fax +39 0384 295084
E-mail: sipol@sipol.com – www.sipol.com
Cap. Soc. € 600.000 i.v. – R.E.A. PV n. 225329
Reg. Imprese di Pavia PV/C.F. 01669490037

P.I. 01842120188

## **Technical Data Sheet**

# **TECHNIPOL® PA 167**

#### **PACKAGING**

25 kg net cardboard boxes, containing 12 reels of around 1.67 kg each.

#### STORAGE

Product is stable for 18 months when stored unopened in its original packaging, kept in a cool and dry place and protected from light. When stocked around  $5 - 10^{\circ}$ C or below, it is recommended to keep it at  $15 - 20^{\circ}$ C for at least for 24 hours before using it.

Version N°: 3.EN Revision n° 0 Revision date: 03/08/2022