P.I. 01842120188



Via L. Da Vinci, 5 – 27036 MORTARA (PV) - ITALY
Tel. +39 0384 295237 – Fax +39 0384 295084
E-mail: sipol@sipol.com – www.sipol.com
Cap. Soc. € 600.000 i.v. – R.E.A. PV n. 225329
Reg. Imprese di Pavia PV/C.F. 01669490037

## **Technical Data Sheet**

# TECHNIPOL® PA 2188

#### DESCRIPTION

TECHNIPOL® PA 2188 is a co-polyamide based thermoplastic adhesive of amber colour, for automotive filter industry. In air engine filter manufacturing it can be used for edge sealing, for reinforcing beads and for pre-filter element bonding. Beside this, in oil engine filter manufacturing it can be used for first/last pleat bonding and for ecological end caps molding. It is characterized by a quick setting time, a good flexibility, a good wettability and a good chemical resistance.


TECHNIPOL® PA 2188 contains more than 80 % of raw materials coming from renewable resources (not-edible).

### **TECHNICAL CHARACTERISTICS**

PROPERTY		TEST METHOD M.U.		VALUE	
Density		ISO 1183	g/cm³	0,98	
Softening point		MI 13	°C	188	
Viscosity Brookfield	232°C	MI 12	Pa*s	4.0	

Cone/ plate Viscometer, Model Brookfield CAP 2000+.

### **VISCOSITY vs TEMPERATURE CURVE**



Version N°: 3.EN Revision n° 1 Revision date: 03/08/2022



Via L. Da Vinci, 5 – 27036 MORTARA (PV) - ITALY
Tel. +39 0384 295237 – Fax +39 0384 295084
E-mail: sipol@sipol.com – www.sipol.com
Cap. Soc. € 600.000 i.v. – R.E.A. PV n. 225329
Reg. Imprese di Pavia PV/C.F. 01669490037

P.I. 01842120188

## **Technical Data Sheet**

# TECHNIPOL® PA 2188

## PROCESSING CONDITIONS

Suggested temperature profile for extrusion

UNDER HOPF	ER FE	EDING ZONE	COMPRESSION ZONE	METERING ZONE	EXTRUSION DIE/ HOSE	NOZZLE
50-80 °C		120-150 °C	170-195 °C	195-210 °C	210-220 °C	210-220 °C

Suggested temperature profile for melters

PRE-HEATING GRID	TANK	HOSE	NOZZLE
210-220 °C	215-225 °C	230-240 °C	230-240 °C

#### **PACKAGING**

25 kg bags equipped with an aluminum film barrier against moisture action. 500 kg cardboard octabins equipped with an inner PE liner. 500 Kg and 1000 Kg big bags.

## STORAGE

Product is stable for 24 months when stored unopened in its original packaging, kept in a cool and dry place and protected from light. When stocked around 5 – 10°C or below, it is recommended to keep it at 15 – 20°C for at least for 24 hours before using it.

Version N°: 3.EN Revision n° 1 Revision date: 03/08/2022